

Blended Look

COLOR BODY • GLAZED PORCELAIN


Wave

COLORS, SIZES & AVAILABILITY

NOMINAL SIZE	FINISH	THICKNESS	GROUT JOINT	ICE	SAND	ASH	SEAWEED	COAL
12 x 24 Rectified	Matte		1/8"	✓	✓	✓	✓	✓
12 x 24 Rectified	Textured		1/8"	⊘	⊘	⊘	⊘	⊘
12 x 24 Rectified Art Decor	Matte		1/8"	✓	✓	✓	✓	✓
24 x 48 Rectified	Matte		1/8"	⊘	⊘	⊘	⊘	⊘
24 x 48 Rectified	Textured		1/8"	⊘	⊘	⊘	⊘	⊘
2 x 2 Mosaic	Matte		N/A	✓	✓	✓	✓	✓
4 x 4 Mosaic	Matte		N/A	⊘	⊘	⊘	⊘	⊘
4 x 4 Mosaic	Textured		N/A	⊘	⊘	⊘	⊘	⊘
2 x 12 Mosaic	Matte		N/A	⊘	⊘	⊘	⊘	⊘
3 x 24 Bullnose	Matte		1/8"	✓	✓	✓	✓	✓
6 x 12 Cove Base	Matte		1/8"	⊘	⊘	⊘	⊘	⊘

✓ Stock Item. ⊘ Non-Stock Item. Requires Extra Lead Time.

TECH INFO

<p>ORIGIN: USA</p> <p>SHADE VARIATION: V3 - Moderate Variation</p> <p>WEAR RATING: Class 5 - Rated for all residential and commercial applications</p> <p>It is not recommended to stagger any tile longer than 15" more than 1/3 the length of the tile.</p> <p> Contains 40% Pre-Consumer Recycled Content. 6% of the Materials and Resources is Post-Consumer Recycled Glass.</p>	R = Residential, LC = Light Commercial, C = Commercial			
	RECOMMENDED APPLICATIONS	R	LC	C
	FLOORS	●	●	●
	WALLS / BACKSPLASH	●	●	●
	POOL DECKING	*	*	⊘
EXTERNAL USE - FROST PROOF	*	*	⊘	

● Approved for this application. * Discuss proper installation method with your Sales Representative.

TILE PERFORMANCE DATA

TECHNICAL FEATURE	NORMS	RESULTS
Water Absorption	ASTM C373	≤ 0.1 %
Breaking Strength	ASTM C648	≥ 400 lbs
Bond Strength	ASTM C482	≥ 200 psi
Dynamic Coefficient of Friction Wet	AcuTest	≥ 0.45 (Matte); 0.65 (Textured)
Thickness Dimension	ASTM C499	In accordance
Facial Dimension	ASTM C499	In accordance
Warpage Diagonal	ASTM C485	In accordance
Wedging	ASTM C502	In accordance
Frost Resistance	ASTM C1026	Frost Proof
Chemical Resistance	ASTM C650	Class A

Always inspect materials prior to installation. Always mix 2-3 cartons at a time while installing to insure the best blend. All product images are representative only. Variation in color and shading is to be expected. Final selection should be made from actual tile samples.